

EXHIBIT G

Table 3: Claims in Parallel Columns with Highlighted Corresponding Terms

Count 1			Corresponding Claims from the Friel Patent (P) and Application (A)
<p>87. A set of different, but mutually compatible fluid prepaints, sufficient to form at least one paint line, which set comprises:</p> <p>(i.) at least one opacifying prepaint comprising at least one opacifying pigment;</p> <p>(ii.) at least one extender prepaint comprising at least one extender pigment; and</p> <p>(iii.) at least one binder prepaint comprising at least one latex polymeric binder.</p>	<p>88. A set of different, but mutually compatible aqueous prepaint compositions, sufficient to form at least one set of paint products, which set comprises:</p> <p>(i) at least one pigment prepaint composition comprising at least one opacifying pigment;</p> <p>(ii) at least one extender prepaint composition comprising at least one extender agent; and</p> <p>(iii) at least one binder prepaint composition comprising at least one polymeric binder.</p>	<p>89. A plurality of varied, but compatible premixed aqueous compositions, sufficient to form a variety of paint compositions, which plurality comprises:</p> <p>(i) at least one premixed pigment composition provided as an aqueous solution comprising an opacifying pigment;</p> <p>(ii) at least one premixed low resin composition provided as an aqueous solution comprising a flattening agent; and</p> <p>(iii) at least one premixed a high resin composition provided as an aqueous solution comprising a resinous binder.</p>	P1, A1

Count 1			Corresponding Claims from the Friel Patent (P) and Application (A)
90. The set of preprints of claim 87, wherein the number of preprints is 3 or more.	91. The set of aqueous preprint compositions of claim 88, wherein the number of preprint compositions is 3 or more.	92. The plurality of premixed aqueous compositions of claim 89, wherein the number of premixed compositions is 3 or more.	P2, A2
93. The set of preprints of claim 87, wherein the opacifying preprint further comprises at least one particulate polymeric binder adsorbed onto the opacifying pigment.	94. The set of aqueous preprint compositions of claim 88, wherein the at least one pigment preprint composition further comprises at least one particulate polymeric binder adsorbed onto the opacifying pigment.	95. The plurality of premixed aqueous compositions of claim 89, wherein the premixed pigment composition further comprises at least one particulate resinous binder adsorbed onto the opacifying pigment.	P3, A3
96. The set of preprints of claim 87, wherein the extender preprint further comprises at least one particulate polymeric binder adsorbed onto the extender pigment.	97. The set of aqueous preprint compositions of claim 88, wherein the at least one extender preprint composition further comprises at least one particulate polymeric binder adsorbed onto the extender agent.	98. The plurality of premixed aqueous compositions of claim 89, wherein the premixed low resin composition further comprises at least one particulate resinous binder adsorbed onto the flattening agent.	P4, A4
99. The set of preprints of claim 87, wherein the extender preprint has a PVC of about 35% to about 100%.	100. The set of aqueous preprint compositions of claim 88, wherein the extender composition has a PVC of about 35% to about 100%.	101. The plurality of premixed aqueous compositions of claim 89, wherein the premixed low resin composition has a PVC of about 35% to about 100%	P49

Count 1			Corresponding Claims from the Friel Patent (P) and Application (A)
<p>102. A paint line produced by a process which comprises the steps of:</p> <p>(a.) providing a set of different, but mutually compatible, fluid prepaints, which set comprises:</p> <p>(i.) at least one opacifying prepaint comprising at least one opacifying pigment,</p> <p>(ii.) at least one extender prepaint comprising at least one extender pigment, and</p> <p>(iii.) at least one binder prepaint comprising at least one latex polymeric binder; and</p> <p>(b.) dispensing a predetermined amount of each of the prepaints into containers to form the paint line.</p>	<p>103. A paint line produced by a process which comprises the steps of:</p> <p>(a) providing a set of different, but mutually compatible, prepaints compositions, which set comprises:</p> <p>(i) at least one pigment prepaint composition as an aqueous solution comprising an opacifying pigment;</p> <p>(ii) at least one low resin prepaint composition as an aqueous solution comprising a extender agent; and</p> <p>(iii) at least one high resin prepaint composition as an aqueous solution comprising a polymeric binder; and</p> <p>(b) dispensing a predetermined amount of each of the prepaint compositions into containers to form an aqueous paint composition of the</p>	<p>104. A plurality of aqueous paint products produced by a process which comprises the steps of :</p> <p>(a) providing a plurality of varied, but compatible premixed pigment compositions as an aqueous solution, which plurality of compositions comprises;</p> <p>(i) at least one premixed pigment composition as an aqueous solution comprising an opacifying pigment;</p> <p>(ii) at least one premixed a low resin composition as an aqueous solution comprising a flattening agent;</p> <p>(iii) at least one premixed high resin composition as an aqueous solution comprising a resinous binder; and</p> <p>(b) dispensing a predetermined amount of each of the premixed compositions into containers to form an aqueous paint product of the plurality of paint products.</p>	P38, A44

Count 1			Corresponding Claims from the Friel Patent (P) and Application (A)
105. A set of different, but mutually compatible, fluid prepaings sufficient to formulate at least one paint line useful for forming pigmented and clear coatings, which set comprises: (i) at least one prepaint comprising at least one opacifying pigment; and (ii) at least two prepaings each of which comprises at least one latex polymeric binder .	106. An plurality of different , but compatible fluid prepaing compositions sufficient to formulate a plurality of aqueous paint compositions useful for forming pigmented and clear coatings, which plurality of prepaing compositions comprising: (i) at least one prepaint composition comprising an opacifying pigment; and (ii) at least two prepaing compositions each of which comprises at least one polymeric binder .	107. A plurality of different but compatible aqueous premixed compositions sufficient to formulate a plurality of paint products useful for forming pigmented coatings, which plurality of premixed compositions comprising: (i) at least one premixed composition as an aqueous solution having an opacifying pigment; (ii) at least two premixed compositions as aqueous solutions each of which comprises at least one resin containing binder .	P45

Count 1			Corresponding Claims from the Friel Patent (P) and Application (A)
108. A method of forming at least one paint line , which method comprises the steps of: (a) providing the set of preprints of claim 105; and (b) dispensing a predetermined amount of each of the preprints into containers or applicators to form the paint line .	109. A method of forming a plurality of aqueous paint compositions , which method comprises the steps of: (a) providing a plurality of the preprint compositions of claim 106; and (b) dispensing a predetermined amount of each of the preprint compositions into containers to form the plurality of paint compositions .	110. A method of forming a plurality of paint products , which method comprises the steps of: (a) providing a plurality of the premixed compositions of claim 107; and (b) dispensing a predetermined amount of each of the premixed compositions into containers to form the plurality of paint products .	P48

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
<p>111. A method of forming at least one paint line, comprising the steps of:</p> <p>(a) providing a set of different, but mutually compatible, fluid prepaints, comprising:</p> <p>(i) at least one opacifying prepaint, comprising at least one opacifying pigment;</p> <p>(ii) at least one extender prepaint comprising at least one extender pigment; and</p> <p>(iii) at least one binder prepaint comprising at least one latex polymeric binder; and</p> <p>(b) dispensing a predetermined amount of each of the prepaints into containers or applicator(s) to form the paint line.</p>	<p>112. A method of forming a plurality of paint products, comprising the steps of:</p> <p>(a) providing a set of varied, but mutually compatible aqueous prepaint compositions, comprising:</p> <p>(i) at least one pigment prepaint composition comprising an opacifying pigment;</p> <p>(ii) at least one extender prepaint composition comprising an extender agent; and</p> <p>(iii) at least one, binder prepaint composition comprising a polymeric binder; and</p> <p>(b) dispensing a predetermined amount of each of the prepaint compositions into containers to form the plurality of paint products.</p>	<p>113. A method of forming a plurality of paint products comprising the steps of:</p> <p>(a) providing a plurality of varied, but compatible premixed aqueous compositions comprising:</p> <p>(i) at least one premixed pigment composition comprising an opacifying pigment;</p> <p>(ii) at least one premixed low resin composition comprising a flattening agent;</p> <p>(iii) at least one premixed high resin composition comprising a resin containing binder; and</p> <p>(b) dispensing a predetermined amount of each of the premixed compositions into containers to form the plurality of paint products.</p>	P5, A5

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
114. The method of claim 111, further comprising the step of mixing the prepaint before, while, or after they are dispensed into the containers.	115. The method of claim 112, further comprising the step of mixing the prepaint compositions before, while, or after they are dispensed into the containers.	116. The method of claim 113, further comprising the step of mixing the premixed compositions before, while, or after they are dispensed into the containers.	P7, A7
117. The method of claim 111, further comprising the step of mixing the prepaint before or while they are dispensed into the applicator(s).	118. The method of claim 112, further comprising the step of mixing the prepaint compositions before or while they are dispensed into the containers.	119. The method of claim 113, further comprising the step of mixing the premixed compositions before or while they are dispensed into the containers.	P8, A8
120. The method of claim 111, further comprising the step of adjusting the viscosity of the prepaints before, while, or after they are dispensed into the containers.	121. The method of claim 112, further comprising the step of adjusting the viscosity of the prepaint compositions before, while, or after they are dispensed into the containers.	122. The method of claim 113, further comprising the step of adjusting the viscosity of the premixed compositions before, while, or after they are dispensed into the containers.	P9, A9
123. The method of claim 111, further comprising the step of adjusting the viscosity of the dispensed prepaints before or while they are dispensed into the applicator(s).	124. The method of claim 112, further comprising the step of adjusting the viscosity of the prepaint compositions before or while they are dispensed into the containers.	125. The method of claim 113, further comprising the step of adjusting the viscosity of the premixed compositions before or while they are dispensed into the containers.	P10, A10

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
126. The method of claim 111, further comprising the step of adding at least one additive that enhances application or final performance of the paint .	127. The method of claim 112, further comprising the step of adding at least one additive that enhances application or final performance of the paint products .	128. The method of claim 113, further comprising the step of adding at least one additive that enhances application or final performance of the paint products .	P11, A11
129. The method of claim 126, wherein the additive is a thickener.	130. The method of claim 127, wherein the additive is a thickener.	131. The method of claim 128, wherein the additive is a thickener.	P13, A13
132. The method of claim 111, further comprising the step of adding at least one colorant to the prepaints .	133. The method of claim 112, further comprising the step of adding at least one colorant to the prepaint compositions .	134. The method of claim 113, further comprising the step of adding at least one colorant to the premixed compositions .	P14, A14
135. The method of claim 111, wherein the opacifying prepaint further comprises at least one particulate polymeric binder absorbed onto the opacifying pigment.	136. The method of claim 112, wherein the pigment composition further comprises at least one particulate polymeric agent absorbed onto the opacifying pigment.	137. The method of claim 113, wherein the pigment composition further comprises at least one particulate resin absorbed onto the opacifying pigment.	P15, A15

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
138. The method of claim 111, wherein the extender prepaint further comprises at least one particulate polymeric binder absorbed onto the extender pigment .	139. The method of claim 112, wherein the extender prepaint composition further comprises at least one particulate polymeric resin absorbed onto the extender agent .	140. The method of claim 113, wherein the low resin composition further comprises at least one particulate resin binder absorbed onto the flattening agent .	P16, A16
141. The method of claim 111, wherein the method is carried out at a paint manufacturing facility.	142. The method of claim 112, wherein the method is carried out at a paint manufacturing facility.	143. The method of claim 113, wherein the method is carried out at a paint manufacturing facility.	P17, A17
144. The method of claim 111, wherein the number of prepaints is 4 or more.	145. The method of claim 112, wherein the number of prepaint compositions is 4 or more.	146. The method of claim 113, wherein the number of premixed compositions is 4 or more.	P18, A21
147. The method of forming at least one paint line of claim 111 wherein the extender prepaint has a PVC of about 35% to about 100%.	148. The method of forming a plurality of paint products claim 112, wherein the extender prepaint composition has a PVC of about 35% to about 100%.	149. The method of forming a plurality of paint products claim 113, wherein the low resin composition has a PVC of about 35% to about 100%.	P50
150. The method of claim 111, wherein the method is carried out at the point-of-sale.	151. The method of claim 112, wherein the method is carried out at the point-of-sale.	152. The method of claim 113, wherein the method is carried out at the point-of-sale.	A18

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
153. The method of claim 111, wherein the method is carried out at the point-of-use.	154. The method of claim 112, wherein the method is carried out at the point-of-use.	155. The method of claim 113, wherein the method is carried out at the point-of-use.	A19
156. The method of claim 111, wherein the method is controlled by a computer.	157. The method of claim 112, wherein the method is controlled by a computer.	158. The method of claim 113, wherein the method is controlled by a computer.	A20

Count 2	Corresponding Claims from the Friel Patent (P) and Application (A)
<p>159. A method of forming a range of paints, the range comprising at least two paint lines, which method comprises the steps of:</p> <p>(a) providing a set of different, but mutually compatible, fluid preprints sufficient to formulate at least two paint lines, which set comprises:</p> <p>(i) at least one opacifying preprint, comprising at least one opacifying pigment;</p> <p>(ii) at least one extender preprint comprising at least one extender pigment;</p> <p>(iii) at least one binder preprint comprising at least one latex polymeric binder; and</p> <p>(iv) at least one additional, different opacifying, extender, or binder preprint selected from the group consisting of (i), (ii), and (iii); and</p> <p>(b) dispensing a predetermined amount of each of the preprints into containers or applicator(s) to form the range of</p>	<p>P6, A6</p> <p>161. A method of forming a range of paint products, the range comprising variations in the plurality of the paint products:</p> <p>(a) providing a plurality of varied, but compatible premixed aqueous compositions sufficient to formulate the at plurality of varied paint products, which plurality comprises:</p> <p>(i) at least one premixed pigment composition comprising an opacifying pigment;</p> <p>(ii) at least one premixed low resin composition comprising a flattening agent;</p> <p>(iii) at least one premixed high resin composition comprising a resin containing binder; and</p> <p>(iv) at least one additional, different premixed pigment, low resin, or high resin composition selected from the group consisting of (i), (ii), and (iii); and</p> <p>(b) dispensing a predetermined amount of each of the premixed compositions into containers to form the plurality of paint products.</p>

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
162. The method of claim 159, further comprising the step of mixing the prepaint before, while, or after they are dispensed into the containers.	163. The method of claim 160, further comprising the step of mixing the prepaint compositions before, while, or after they are dispensed into the containers.	164. The method of claim 161, further comprising the step of mixing the premixed compositions before, while, or after they are dispensed into the containers.	P7, A7
165. The method of claim 159, further comprising the step of mixing the prepaint before or while they are dispensed into the applicator(s).	166. The method of claim 160, further comprising the step of mixing the prepaint compositions before or while they are dispensed into the containers.	167. The method of claim 161, further comprising the step of mixing the premixed compositions before or while they are dispensed into the containers.	P8, A8
168. The method of claim 159, further comprising the step of adjusting the viscosity of the prepaints before, while, or after they are dispensed into the containers.	169. The method of claim 160, further comprising the step of adjusting the viscosity of the prepaint compositions before, while, or after they are dispensed into the containers.	170. The method of claim 161, further comprising the step of adjusting the viscosity of the premixed compositions before, while, or after they are dispensed into the containers.	P9, A9
171. The method of claim 159, further comprising the step of adjusting the viscosity of the dispensed prepaints before or while they are dispensed into the applicator(s).	172. The method of claim 160, further comprising the step of adjusting the viscosity of the prepaint compositions before or while they are dispensed into the containers.	173. The method of claim 161, further comprising the step of adjusting the viscosity of the premixed compositions before or while they are dispensed into the containers.	P10, A10

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
174. The method of claim 159, further comprising the step of adding at least one additive that enhances application or final performance of the paint .	175. The method of claim 160, further comprising the step of adding at least one additive that enhances application or final performance of the paint products .	176. The method of claim 161, further comprising the step of adding at least one additive that enhances application or final performance of the paint products .	P11, A11
177. The method of claim 174, wherein the additive is a thickener.	178. The method of claim 175, wherein the additive is a thickener.	179. The method of claim 176, wherein the additive is a thickener.	
180. The method of claim 159, further comprising the step of adding at least one colorant to the prepaints .	181. The method of claim 160, further comprising the step of adding at least one colorant to the prepaint compositions .	182. The method of claim 161, further comprising the step of adding at least one colorant to the premixed compositions .	P13, A13
183. The method of claim 159, wherein the opacifying prepaint further comprises at least one particulate polymeric binder absorbed onto the opacifying pigment.	184. The method of claim 160, wherein the pigment composition further comprises at least one particulate polymeric agent absorbed onto the opacifying pigment.	185. The method of claim 161, wherein the pigment composition further comprises at least one particulate resin absorbed onto the opacifying pigment.	P14, A14
			P15, A15

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
186. The method of claim 159, wherein the extender prepaint further comprises at least one particulate polymeric binder absorbed onto the extender pigment .	187. The method of claim 160, wherein the extender prepaint composition further comprises at least one particulate polymeric resin absorbed onto the extender agent .	188. The method of claim 161, wherein the low resin composition further comprises at least one particulate resin binder absorbed onto the flattening agent .	P16, A16
189. The method of claim 159, wherein the method is carried out at a paint manufacturing facility.	190. The method of claim 160, wherein the method is carried out at a paint manufacturing facility.	191. The method of claim 161, wherein the method is carried out at a paint manufacturing facility.	P17, A17
192. The method of claim 159, wherein the number of prepaints is 4 or more.	193. The method of claim 160, wherein the number of prepaint compositions is 4 or more.	194. The method of claim 161, wherein the number of premixed compositions is 4 or more.	P18, A21
195. The method of forming at least one paint line of claim 159 wherein the extender prepaint has a PVC of about 35% to about 100%.	196. The method of forming a plurality of paint products claim 160, wherein the extender prepaint composition has a PVC of about 35% to about 100%.	197. The method of forming a plurality of paint products claim 161, wherein the low resin composition has a PVC of about 35% to about 100%.	P50
198. The method of claim 159, wherein the method is carried out at the point-of-sale.	199. The method of claim 160, wherein the method is carried out at the point-of-sale.	200. The method of claim 161, wherein the method is carried out at the point-of-sale.	A18

Count 2			Corresponding Claims from the Friel Patent (P) and Application (A)
201. The method of claim 159, wherein the method is carried out at the point-of-use.	202. The method of claim 160, wherein the method is carried out at the point-of-use.	203. The method of claim 161, wherein the method is carried out at the point-of-use.	A19
204. The method of claim 159, wherein the method is controlled by a computer.	205. The method of claim 160, wherein the method is controlled by a computer.	206. The method of claim 161, wherein the method is controlled by a computer.	A20

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
<p>207. A fluid opacifying prepaint useful for formulating a one pack, pigmented latex paint having a volume solids content of about 30% to about 70% and a Stormer viscosity of about 50 to about 250 KU, which prepaint contains other paint ingredients, which prepaint consists essentially of:</p> <p>(i) at least one opacifying pigment, (ii) at least one dispersant,</p> <p>(iii) at least one thickener, and</p> <p>(iv) water;</p> <p>wherein the dispersant(s) and the thickener(s) are mutually compatible with the pigment(s) and with the other paint ingredients.</p>	<p>208. A premixed aqueous pigment composition useful for formulating a one pack, pigmented aqueous paint composition having a volume solids content of about 30% to about 70% and a Stormer viscosity of about 50 to about 250 KU, which premixed composition contains other paint ingredients, which premixed aqueous composition consists essentially of:</p> <p>(i) at least one opacifying pigment,</p> <p>(ii) at least one dispersant,</p> <p>(iii) at least one thickener, and</p> <p>(iv) water;</p> <p>wherein the dispersant(s) and the thickener(s) are mutually compatible with the pigment(s) and with the other paint composition ingredients.</p>	P19, A22

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
209. The prepaint of claim 207 wherein the volume solids content is about 35% to about 50% and the Stormer viscosity is about 60 to about 150 KU.	210. The premixed aqueous pigment composition of claim 208, wherein the volume solids content is about 35% to about 50% and the Stormer viscosity is about 60 to about 150 KU.	P20, A23
211. The prepaint of claim 207, wherein the opacifying pigment comprises titanium dioxide.	212. The premixed aqueous pigment composition of claim 208, wherein the opacifying pigment comprises titanium dioxide.	P24, A27
213. The prepaint of claim 207, wherein the dispersant comprises potassium tripolyphosphate.	214. The premixed aqueous pigment composition of claim 208, wherein the dispersant comprises potassium tripolyphosphate.	P27, A30
215. The prepaint of claim 207, wherein the thickener comprises a cellulosic.	216. The premixed aqueous pigment composition of claim 208, wherein the thickener a cellulosic.	P28, A31

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
217. The prepaint of claim 207, further consisting essentially of at least one additive comprising a coalescent, with the additive being present in an amount of less than about 10% by weight, based on the total weight of the prepaint.	218. The premixed aqueous pigment composition of claim 208, further consisting essentially of at least one additive comprising a coalescent, with the additive being present in an amount of less than about 10% by weight, based on the total weight of the premixed aqueous pigment composition.	P30, A34

Count 3	Corresponding Claims from the Friel Patent (P) and Application (A)
<p>219. A set of two different, but mutually compatible fluid prepaints useful for formulating a latex paint, which set comprises:</p> <p>(a) the opacifying prepaint of claim 207; and</p> <p>(b) a latex polymeric binder prepaint having volume solids content of about 25% to about 66.5% or a Brookfield viscosity of less than about 100,000 centipoise at a shear rate of 1.25 reciprocal seconds, which prepaint consists essentially of a water-borne latex polymeric binder having a Tg of about -430.degree. C. to about 70.degree. C. and water;</p> <p>wherein the prepaint ingredients are mutually compatible with each other and with the ingredients of the other prepaint in the set.</p>	<p>220. A set of two different, but mutually compatible premixed aqueous compositions useful for formulating an aqueous paint combination, which set comprises:</p> <p>(a) the premixed aqueous pigment composition of claim 208; and</p> <p>(b) a premixed polymeric binder composition having volume solids content of about 25% to about 70% or a Brookfield viscosity of less than about 100,000 centipoise at a shear rate of 1.25 reciprocal seconds, which binder composition consists essentially of a water-borne resin containing binder having a Tg of about -430.degree. C. to about 70.degree. C. and water;</p> <p>wherein the ingredients of the premixed compositions are mutually compatible with each other and with the ingredients of the other premixed compositions in the set.</p>

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
<p>221. The set of prepaints of claim 219, wherein the binder prepaint has a volume solids content of about 30 to about 65% and a Brookfield viscosity of about 100 to about 50,000 centipoise at a shear rate of 1.25 reciprocal seconds, and consists essentially of a water-borne polymeric binder having a Tg of about -10 to about 60.degree. C.</p>	<p>222. The set of premixed aqueous compositions of claim 220, wherein the premixed binder composition has a volume solids content of about 30 to about 65% and a Brookfield viscosity of about 100 to about 50,000 centipoise at a shear rate of 1.25 reciprocal seconds, and consists essentially of a water-borne resin containing binder having a Tg of about -10 to about 60.degree. C.</p>	P33, A38
<p>223. The set of prepaints of claim 219, wherein the binder prepaint further consists essentially of at least one additive comprising a coalescent, the additive being present in an amount of less than about 10% by weight, based on the total weight of the binder prepaint.</p>	<p>224. The set of premixed aqueous compositions of claim 220, wherein the premixed binder composition further consists essentially of at least one additive comprising a coalescent, the additive being present in an amount of less than about 10% by weight, based on the total weight of the premixed binder composition.</p>	

Count 3	Corresponding Claims from the Friel Patent (P) and Application (A)
<p>225. A set of three different, but mutually compatible, fluid preprints, useful for formulating a latex paint, which set comprises:</p> <p>(a) the set of preprints of claim 219; and</p> <p>(b) a fluid pigment extender preprint which consists essentially of:</p> <p>(i) at least one mineral extender,</p> <p>(ii) at least one thickener,</p> <p>(iii) water, and</p> <p>(iv) optionally a polymeric binder;</p> <p>wherein the binder preprint has a volume solids content of about 30% to about 70%, a PVC of about 35% to about 100%, and a Stormer viscosity of about 50 to about 250 KU.</p>	<p>226. A set of three different, but mutually compatible, premixed aqueous compositions, useful for formulating a paint product, which set comprises:</p> <p>(a) the set of premixed compositions of claim 220; and</p> <p>(b) a premixed aqueous pigment extender composition which consists essentially of:</p> <p>(i) at least calcined clay,</p> <p>(ii) at least one thickener,</p> <p>(iii) water, and</p> <p>(iv) optionally a resin containing binder;</p> <p>wherein the premixed binder composition has a volume solids content of about 30% to about 70%, a PVC of about 35% to about 100%, and a Stormer viscosity of about 50 to about 250 KU.</p>

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
227. The set of prepaints of claim 225, wherein the extender prepaint has a volume solids content of about 35% to about 65%, a PVC of about 40% to about 100% and a Stormer viscosity of about 60 to about 150 KU.	228. The set of premixed aqueous compositions of claim 226, wherein the premixed aqueous extender composition has a volume solids content of about 35% to about 65%, a PVC of about 40% to about 100% and a Stormer viscosity of about 60 to about 150 KU.	P36, A42
229. The set of prepaints of claim 219, wherein the binder prepaint further consists essentially of at least one additive comprising a coalescent, with the additive being present in an amount of less than about 20% by weight, based on the total weight of the binder prepaint .	230. The set of premixed aqueous compositions of claim 220, wherein the premixed binder composition further consists essentially of at least one additive comprising a coalescent, with the additive being present in an amount of less than about 20% by weight, based on the total weight of the premixed binder composition .	P37, A43

Count 3	Corresponding Claims from the Friel Patent (P) and Application (A)
<p>231. A fluid white opacifying prepaint having a volume solids content of about 30% to about 70%, a PVC of about 35% to about 100%, and a Stormer viscosity of about 50 to about 250 KU, useful for formulating a one pack, pigmented latex paint containing other paint ingredients, which prepaint consists essentially of:</p> <ul style="list-style-type: none"> (i) at least one opacifying pigment, (ii) at least one dispersant, (iii) at least one thickener, (iv) at least one film-forming or non-film-forming polymer, and (v) water; wherein the dispersant(s), the thickener(s), the thickener(s), and the polymer(s) are compatible with the pigment(s) and with the other premixed aqueous composition ingredients and wherein the premixed aqueous composition is stable to sedimentation. 	<p>232. A premixed aqueous pigment composition having a volume solids content of about 30% to about 70%, a PVC of about 35% to about 100%, and a Stormer viscosity of about 50 to about 250 KU, useful for formulating a one pack, pigmented aqueous paint product containing other paint ingredients, which premixed aqueous composition consists essentially of:</p> <ul style="list-style-type: none"> (i) at least one opacifying pigment, (ii) at least one dispersant, (iii) at least one thickener, (iv) at least one film-forming or non-film-forming resin, and (v) water; wherein the dispersant(s), the thickener(s), and the polymer(s) are compatible with the pigment(s) and with the other premixed aqueous composition ingredients and wherein the premixed aqueous composition is stable to sedimentation.

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
233. The prepaint of claim 231, wherein the volume solids content is about 35% to about 50%, the PVC is about 50 to about 100%, and the Stormer viscosity is about 60 to about 150 KU.	234. The premixed composition of claim 232, wherein the volume solids content is about 35% to about 50%, the PVC is about 50 to about 100%, and the Stormer viscosity is about 60 to about 150 KU.	P22, A25
235. The prepaint of claim 231, wherein the polymer is adsorbed onto the opacifying pigment.	236. The premixed resin composition of claim 232, wherein the resin is adsorbed onto the opacifying pigment.	P23, A26
237. The prepaint of claim 231, wherein the opacifying pigment comprises titanium dioxide.	238. The premixed composition of claim 232, wherein the opacifying pigment comprises titanium dioxide.	P24, A27
239. The prepaint of claim 231, wherein the dispersant comprises potassium triphosphate.	240. The premixed composition of claim 232, wherein the dispersant comprises potassium triphosphate.	P27, A30
241. The prepaint of claim 231, wherein the thickener comprises a cellulosic.	242. The premixed composition of claim 232, wherein the thickener comprises a cellulosic.	P28, A31
243. The prepaint of claim 231, wherein the polymer comprises an acrylic polymer .	244. The premixed composition of claim 232, wherein the resin comprises an acrylic resin .	P29, A32 & A33

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
245. The prepaint of claim 231, further consisting essentially of at least one additive comprising a coalescent, with the additive being present in an amount of less than about 10% by weight, based on the total weight of the prepaint .	246. The premixed composition of claim 232, further consisting essentially of at least one additive comprising a coalescent, with the additive being present in an amount of less than about 10% by weight, based on the total weight of the premixed composition .	P30, A34

Count 3	Corresponding Claims from the Friel Patent (P) and Application (A)
<p>247. A set of two different, but mutually compatible fluid prepaits useful for formulating a latex paint, which set comprises:</p> <p>(a) the opacifying prepaint of claim 231; and</p> <p>(b) a latex polymeric binder prepaint having volume solids content of about 25% to about 70% or a Brookfield viscosity of less than about 100,000 centipoise at a shear rate of 1.25 reciprocal seconds, which binder prepaint consists essentially of a water-borne latex polymeric binder having a Tg of about -430.degree. C. to about 70.degree. C. and water;</p> <p>wherein the prepaint ingredients are mutually compatible with each other and with the ingredients of the other prepaint in the set.</p>	<p>248. A set of two different, but mutually compatible premixed aqueous compositions useful for formulating a paint composition, which set comprises:</p> <p>(a) the premixed pigment composition of claim 232; and</p> <p>(b) a premixed polymeric binder composition having volume solids content of about 25% to about 70% or a Brookfield viscosity of less than about 100,000 centipoise at a shear rate of 1.25 reciprocal seconds, which premixed binder composition consists essentially of a water-borne resin containing binder having a Tg of about -430.degree. C. to about 70.degree. C. and water;</p> <p>wherein the ingredients of the premixed compositions are mutually compatible with each other and with the ingredients of the other</p>

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
249. The set of prepaints of claim 247, wherein the binder prepaint has a volume solids content of about 30 to about 65% and a Brookfield viscosity of about 100 to about 50,000 centipoise at a shear rate of 1.25 reciprocal seconds, and consists essentially of a water-borne polymeric binder having a Tg of about -10 to about 60.degree. C.	250. The set of premixed compositions of claim 248, wherein the premixed binder composition has a volume solids content of about 30 to about 65% and a Brookfield viscosity of about 100 to about 50,000 centipoise at a shear rate of 1.25 reciprocal seconds, and consists essentially of a water-borne resin containing binder having a Tg of about -10 to about 60.degree. C.	P33, A38
251. The set of prepaints of claim 247, wherein the binder prepaint further consists essentially of at least one additive comprising a coalescent, the additive being present in an amount of less than about 10% by weight, based on the total weight of the binder prepaint .	252. The set of premixed compositions of claim 248, wherein the premixed binder composition further consists essentially of at least one additive comprising a coalescent, the additive being present in an amount of less than about 10% by weight, based on the total weight of the premixed binder composition .	P34, A39

Count 3	Corresponding Claims from the Friel Patent (P) and Application (A)
<p>253. A set of three different, but mutually compatible, fluid prepaings, useful for formulating a latex paint, which set comprises:</p> <p>(a) the set of prepaings of claim 247; and</p> <p>(b) a fluid pigment extender prepaing which consists essentially of:</p> <p>(i) at least one mineral extender,</p> <p>(ii) at least one thickener,</p> <p>(iii) water, and</p> <p>(iv) optionally a polymeric binder;</p> <p>wherein the binder prepaing has a volume solids content of about 30% to about 70%, a PVC of about 35% to about 100%, and a Stormer viscosity of about 50 to about 250 KU.</p>	<p>254. A set of three different, but mutually compatible, premixed aqueous compositions, useful for formulating a paint product, which set comprises:</p> <p>(a) the set of premixed compositions of claim 248; and</p> <p>(b) a premixed aqueous pigment extender composition which consists essentially of:</p> <p>(i) at least calcined clay,</p> <p>(ii) at least one thickener,</p> <p>(iii) water, and</p> <p>(iv) optionally a resin containing binder;</p> <p>wherein the premixed binder composition has a volume solids content of about 30% to about 70%, a PVC of about 35% to about 100%, and a Stormer viscosity of about 50 to about 250 KU.</p>

Count 3		Corresponding Claims from the Friel Patent (P) and Application (A)
255. The set of prepaints of claim 253, wherein the extender prepaint has a volume solids content of about 35% to about 65%, a PVC of about 40% to about 100% and a Stormer viscosity of about 60 to about 150 KU.	256. The set of premixed aqueous compositions of claim 254, wherein the premixed extender composition has a volume solids content of about 35% to about 65%, a PVC of about 40% to about 100% and a Stormer viscosity of about 60 to about 150 KU.	P36, A42
257. The set of prepaints of claim 247, wherein the binder prepaint further consists essentially of at least one additive comprising a coalescent, with the additive being present in an amount of less than about 20% by weight, based on the total weight of the binder prepaint .	258. The set of premixed aqueous compositions of claim 248, wherein the premixed binder composition further consists essentially of at least one additive comprising a coalescent, with the additive being present in an amount of less than about 20% by weight, based on the total weight of the premixed binder composition .	P37, A43

Count 4	Corresponding Claims from the Friel Patent (P) and Application (A)
<p>259. A fluid pigment extender prepaint, useful for formulating a one pack, pigmented latex paint containing other paint ingredients, which prepaint consists essentially of:</p> <ul style="list-style-type: none"> (i) at least one mineral extender having a volume solids content of about 30% to about 70%, a PVC of about 35% to about 100%, and a Stormer viscosity of about 50 to about 250 KU; (ii) at least one thickener, (iii) water, and (iv) an optional polymeric binder; wherein the prepaint ingredients are compatible with each other and with the ingredients of the paint. 	<p>260. A premixed aqueous pigment extender composition, useful for producing a pigmented aqueous paint product containing other paint ingredients, which premixed composition consists essentially of:</p> <ul style="list-style-type: none"> (i) at least one calcined clay having a volume solids content of about 30% to about 70%, a PVC of about 35% to about 100%, and a Stormer viscosity of about 50 to about 250 KU; (ii) at least one thickener, (iii) water, and (iv) an optional polymeric resin containing binder; wherein the premixed composition ingredients are compatible with each other and with the ingredients of the paint product.